Supplier - SMART OIL Smart Base RP3314

Corrosion Inhibitor For Copper

Typical Properties

Appearance Specific Gravity@25°C Viscosity@40°C, cSt Flash Point C.O.C., °C Std Packaging (NW / GW, Kg)

Product Description

The base material of **SMART BASE RP3314** is benzotriazole. It belongs to a multifunctional type.

SMART BASE RP3314 can be added to formulations with active sulfur to inhibit copper corrosion. It can be blended with base oil or mineral oil to make rust preventive oil, and can be added to soluble oil formulation to protect yellow metals from corrosion.

Suggested formulation

- Drawing and stamping oil: 0.5-2% in 68cSt oil;
- Corrosion Preventive oil for Copper: 6% in 150SN base oil or volatile solvent.

Applications General Application Suggested Treat Rates, %wt 1 - 20

Print date: 04-02-25

Disclaimer: Information provided by this website and product page including specifications, applications and formulations are based on tests and data supplied by Smart Oil companies, manufacturers or any of our collaborated companies or suppliers, which are believed to be correct and reliable at the time of writing and data update. However, Smart Oil companies, manufacturers or any of our collaborated companies or suppliers make no warranty or responsibility, express or implied, of any kind regarding products, performance, formulations or applications, as operation conditions and application environments are beyond our control, or products will be modified by action of manufacturers or due to change in market environments. Users are herewith expressively requested to conduct test to determine the suitability of our products or product information before use. Furthermore, we regret that we cannot be responsible for informing customers any changes in specifications, formulations, or other technical contents on this website and product page. Also, We hereby state that all product trademarks other than Smart Oil, including trademarks from our , suppliers are the trademarks belong to the respective companies, or from their sources.

Deep Amber Liquid 0.900 - 1.000 200 - 400 ≥ 160 217.0 / 200.0